

We claim as follows:

1. A method of producing a polymer-clay nanocomposite, comprising the steps of:
providing a supply of polymer-clay mixture;
exfoliating the mixture through solid-state shear pulverization in the
5 presence of cooling sufficient to maintain the extruded mixture in the solid state
during the pulverization; and
discharging the resulting exfoliated mixture.
2. The method of claim 1, further comprising the step of melt-extruding the
10 polymer-clay mixture prior to said step of exfoliating.
3. The method of claim 1, wherein the polymer-clay mixture comprises at least
about 3% organoclay.
- 15 4. The method of claim 1, wherein the polymer-clay mixture comprises about 10%
organoclay.
5. The method of claim 3, wherein the organoclay contains between about 40-50%
clay and between about 50-60% organic content.
20
6. The method of claim 5, wherein the organoclay is a montmorillonite.
7. The method of claim 1, wherein the polymer-clay mixture comprises a polymer
selected from the group consisting of polypropylene, polyolefins, polystyrene,
25 polymethacrylates, poly(ethylene-co-vinyl acetate), polyhydroxystyrene, poly
(vinyl pyridine), polyvinylalcohol, polyacrylamide, polycaprolactone, copolymers
of ethylene, copolymers of propylene, copolymers of acetate, poly (ethylene
terephthalate), nylon, and blends thereof.
- 30 8. The method of claim 1, including the step of cooling a pulverizer barrel with a
chilled fluid at about 10° Celsius during the pulverization.

9. A polymer-clay nanocomposite, comprising:
a nonpolar polymer material; and
at least about 3% highly exfoliated organoclay.
- 5
10. The nanocomposite of claim 9, wherein said nonpolar polymer material is selected from the group consisting of polypropylene, polyethylene, polystyrene, copolymers of propylene, copolymers of ethylene, and blends thereof.
- 10
11. The nanocomposite of claim 9, wherein said nonpolar polymer material is a polyolefin.
12. The nanocomposite of claim 9, wherein said organoclay comprises between about 40-50% clay content and between about 50-60% organic content.
- 15
13. The nanocomposite of claim 12, wherein said organoclay is a montmorillonite.
14. The nanocomposite of claim 13, wherein said organoclay has:
40-50% nanoclay content,
a density of 38-48 lbs/ft³, and
a maximum of 0.2% moisture content.
- 20
15. The nanocomposite of claim 9, including about 10% highly exfoliated organoclay.
- 25
16. A method of producing a polymer hybrid nanocomposite, comprising the steps of:
providing a supply of polymer material;
mixing the polymer material with a reinforcing material to form a mixture;

effecting a high level of dispersion of the reinforcing material throughout the mixture through solid-state shear pulverization in the presence of cooling sufficient to maintain the mixture in the solid state during the pulverization; and discharging the resulting mixture.

5

17. The method of claim 16, wherein the reinforcing material is selected from the group consisting of a metal, carbon, silicate and cellulose.